



52600

*Super Seal Premium
Crack Filler
Technical Data Sheet*

**1 Gal Super Seal
Premium Crack Filler™**

Item#: 52600
UPC #: 09032 52600 6

Section I - PHYSICAL PROPERTIES & PERFORMANCE

Appearance: Brown Liquid dries black.	Maximum VOC: Less than 10 g/l
Application Temperature: 55° F and rising.	Specific Gravity: 1.3-1.5
Viscosity: 4,000-7,000 cps	Weight Per Gallon: 7.8-8.6
Color: Brown	Consistency: Thick liquid
Boiling Point: >212° F	Cure Time (50% relative humidity, 70° F): 24-48 hours.
Freeze ability: Do not allow to freeze.	Container Size & Weight: 1 gallon, 8.2 lbs. per gallon

Section II – FEATURES

Super Seal Premium Crack Filler™ is a specially formulated Acrylic Latex Rubber. Vinyl Polymer Blend that provides extended life & greater durability than ordinary cold pour formula crack fillers. **FEATURES:** Fast dry additive accelerates drying & curing time. For blacktop cracks up to 1/2" wide. Fortified with acrylic rubber for maximum flexibility and bond. Fast dry formula for faster set-up. Just clean crack, shake, snip open and squeeze into crack. Low VOC Formula.

Section III - SURFACE PREPARATION

Super Seal Premium Crack Filler™ is a simple and clean process. Before applying the product, it is important to thoroughly clean out the crack and remove any loose debris. Rinsing the crack and allowing it to dry will give you the best results.

Section IV – APPLICATION

Super Seal Premium Crack Filler™ is easy to use. Remove all dirt, grass, old crack filler and debris from crack to be filled. Shake well before using. Pre-mixed, **DO NOT DILUTE**. Cut tip to a size slightly smaller than the width for the crack to be repaired. Squeeze/pour crack filler **SLOWLY** into crack overfilling slightly to allow for shrinkage. The filler will self-level. Wipe clean any crack filler residue from crack surface. (If you leave any on the outside of the crack it will track on a hot day!). Do not apply more than 1/4" thick in any single application. If you have larger cracks you may first clean them, then fill with a backer rod to within 1/4" of surface before applying Super Seal Premium Crack Filler™. Super Seal Premium Crack Filler™ will dry to the touch within 30 minutes and depending on weather, should be fully dry within 4-8 hours and ready to seal over. Use when outdoor and surface temp is 55 degrees F or higher and if no rain is forecast within 24 hours. Cleans up with soap and water. Do not allow to freeze. Keep out of reach of children. Not flammable. Keep cap on when not in use.

Section V - PRECAUTIONS

Avoid applying when rainfall is likely within 24 hours of application time. Avoid applying when temperatures drop below 55° F. Allow all repaired surfaces to cure 24 hours prior to sealing. For crack fillers you should wait 24 hours. If the crack filler is firm you may seal over. When transporting this product, ensure that the container is secured and the lid is secure. Do not allow the container to tumble as this may loosen the lid and allow leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Protective clothing and eyewear should be used during application.

Section VI - CLEAN UP & STORAGE

Fresh crack filler will clean up with soap and water.

Section VII - !!!CAUTION!!!

Super Seal Premium Crack Filler™ is for exterior use only. Keep out of reach of children. Keep container capped when not in use. Non-flammable. This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

Emergency & First Aid Procedures:

Eyes: Immediately flush with clean water for 15 minutes while holding eyelids open; consult a physician.

Inhalation: If overcome by mist or vapor, remove from exposure immediately; call a physician. If breathing is stopped or irregular, start resuscitation, administer oxygen.

Skin: Remove any contaminated clothing and wash skin with soap and warm water. Vegetable or mineral oil can remove dry material.

Ingestion: DO NOT INDUCE VOMITTING even though vomiting may occur. If vomiting occurs, keep head below hips to prevent aspiration of liquid into the lungs. Get immediate medical attention.

Section VIII - WARRANTY AND DISCLAIMER

The methods and techniques described herein represent some that have been used successfully to obtain desired results. Allow new pavement to fully cure—we recommend a minimum of 12 months prior to sealing. If water “beads up” on pavement it has not fully cured. All variations in asphalt, climate conditions and equipment cannot be anticipated. The decision to use any of these methods and techniques is entirely at the election and responsibility of the user. Sealer is warranted from defects for a period stated on the pail from date of purchase when applied according to our application instructions. Since sealer cannot control the manner of use of its products after their sale, seller will not be responsible for any consequential or indirect damages. Manufacturer disclaims liability for areas that are flat, have ponding waters, poor drainage or snow removal damage. If product is deemed defective, it shall be replaced. No warranties will apply if the goods are in any way altered or modified after delivery by seller. There are no express warranties which extend beyond the description on the face hereof, manufacturer disclaims any implied warranties. This warranty does not include labor costs incurred for the application, re-application or consequential damage costs. Failures due to acts of God, fire, structural defects or causes beyond our control are excluded from this warranty. If repair products were used, repair products must be used for warranty to be honored. Two coats must be applied to validate warranty. Not applicable on commercial parking lots. This warranty gives you specific rights and you may also have other rights which may vary from state to state. Original proof of purchase required for warranty claims.